



Color Copy coated glossy has a coating specially adapted to digital colour laser printing with a unique gloss effect. It is especially suitable for leaflets, annual reports and brochures.



**Technical Data:** Color Copy coated glossy

			135	170	200	250	300	350
<b>Basis weight</b>	g/m <sup>2</sup>	ISO 536	<b>135</b> ± 3.0	<b>170</b> ± 4.0	<b>200</b> ± 6.0	<b>250</b> ± 8.0	<b>300</b> ± 10.0	<b>350</b> ± 12.0
<b>Caliper</b>	µm	ISO 534	<b>107</b> ± 4	<b>136</b> ± 6	<b>162</b> ± 7	<b>213</b> ± 9	<b>260</b> ± 11	<b>312</b> ± 14
<b>Stiffness 15°/10mm</b>	MD mN	ISO 2493-1	<b>180</b> ± 20					
<b>Stiffness 15°/10mm</b>	CD mN	ISO 2493-1	<b>80</b> ± 8					
<b>Smoothness Bekk</b>	sec	ISO 5627	<b>1000</b> ± 300	<b>500</b> ± 150	<b>400</b> ± 120	<b>250</b> ± 75	<b>180</b> ± 60	<b>180</b> ± 60
<b>Opacity</b>	%	ISO 2471	<b>min 94.0</b>	<b>min 96.0</b>	<b>min 98.0</b>	<b>min 99.0</b>		
<b>Moisture abs.</b>	%	ISO 287	<b>4.8</b> ± .6	<b>4.8</b> ± .6	<b>4.8</b> ± .6	<b>4.8</b> ± .6	<b>4.8</b> ± .6	<b>4.8</b> ± .6
<b>Brightness UV</b>	%	ISO 2470	<b>103.0</b> ± 2.0	<b>103.0</b> ± 2.0	<b>103.0</b> ± 2.0	<b>103.0</b> ± 2.0	<b>103.0</b> ± 2.0	<b>103.0</b> ± 2.0
<b>CIE Whiteness</b>	%	ISO 11475	<b>139</b> ± 2.5	<b>139</b> ± 2.5	<b>139</b> ± 2.5	<b>139</b> ± 2.5	<b>139</b> ± 2.5	<b>139</b> ± 2.5
<b>Gloss 75°</b>	TS %	TAPPI T 480	<b>75</b> ± 4	<b>75</b> ± 4	<b>75</b> ± 4	<b>75</b> ± 4	<b>75</b> ± 4	<b>75</b> ± 4

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001. Standard measurement uncertainty between laboratories is not incorporated.

SIGNIFICANCE OF VALUES: 2 SIGMA